

(19) 世界知的所有権機関
国際事務局



(43) 国際公開日
2005 年 1 月 27 日 (27.01.2005)

PCT

(10) 国際公開番号
WO 2005/007577 A1

(51) 国際特許分類⁷: C01G 53/00, H01M 4/02, 4/58, 10/40

(21) 国際出願番号: PCT/JP2004/010238

(22) 国際出願日: 2004 年 7 月 12 日 (12.07.2004)

(25) 国際出願の言語: 日本語

(26) 国際公開の言語: 日本語

(30) 優先権データ:
特願2003-199205 2003 年 7 月 18 日 (18.07.2003) JP
特願2003-208657 2003 年 8 月 25 日 (25.08.2003) JP

(71) 出願人(米国を除く全ての指定国について): 東ソー株式会社 (TOSOH CORPORATION) [JP/JP]; 〒746-8501 山口県 周南市 開成町 4 5 6 0 番地 Yamaguchi (JP).

(72) 発明者: および


(75) 発明者/出願人(米国についてのみ): 藤井 康浩 (FUJII, Yasuhiro) [JP/JP]; 〒745-0851 山口県 周南市 大字徳山 5 5 3 6 番地 Yamaguchi (JP). 鈴木 直人 (SUZUKI, Naoto) [JP/JP]; 〒746-0024 山口県 周南市 古泉 2-1 7-2 Yamaguchi (JP). 庄司 孝之 (SHOJI, Takayuki) [JP/JP]; 〒746-0011 山口県 周南市 土井 2 丁目 1 5-4-1 0 2 Yamaguchi (JP). 国吉 実 (KUNIYOSHI, Minoru) [JP/JP]; 〒753-0212 山口県 山口市 下小鶴字山ノ神 8 8 7-3 7 Yamaguchi (JP). 岩田 英一 (IWATA, Eiichi) [JP/JP]; 〒746-0011 山口県 周南市 土井 2 丁目 1 5-4-2 0 5 Yamaguchi (JP).

(74) 代理人: 小栗 昌平, 外(OGURI, Shohel et al.); 〒107-6013 東京都 港区 赤坂一丁目 1 2 番 3 2 号 アーク森ビル 1 3 階 栄光特許事務所 Tokyo (JP).

[続葉有]

(54) Title: LITHIUM-NICKEL-MANGANESE COMPOSITE OXIDE, PROCESS FOR PRODUCING THE SAME AND USE THEREOF

(54) 発明の名称: リチウム-ニッケル-マンガン複合酸化物及びその製造方法並びにその用途



(57) Abstract: A positive electrode material for lithium ion secondary battery, exhibiting high discharge capacity and excelling in rate characteristics and cycle characteristics. The battery is characterized in that a lithium-nickel-manganese composite oxide wherein the composition is represented by the formula $\text{Li}_x\text{Ni}_y\text{Mn}_z\text{O}_2$ (wherein x is $1+1/9 \pm (1+1/9)$, y is $4/9 \pm (4/9)/10$ and z is $4/9 \pm (4/9)/10$), the crystal structure belongs to a monoclinic system and the space group is C12/m1 (No. 12) is used as a positive electrode material. With respect to the lithium-nickel-manganese composite oxide, it is preferred that on face (002) and face (13-3) in Miller index hkl at monoclinic system C12/m1 (No. 12) attribution, the powder X-ray diffraction peak intensity ratio $I_{(002)}/I_{(13-3)}$ measured with the use of Cu-K α rays be 1.35 or higher.

[続葉有]



(81) 指定国 (表示のない限り、全ての種類の国内保護が可能): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MY, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SI, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

KG, KZ, MD, RU, TJ, TM), ヨーロッパ (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

添付公開書類:
— 国際調査報告書

(84) 指定国 (表示のない限り、全ての種類の広域保護が可能): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SI, SZ, TZ, UG, ZM, ZW), ユーラシア (AM, AZ, BY,

2文字コード及び他の略語については、定期発行される各PCTガゼットの巻頭に掲載されている「コードと略語のガイダンスノート」を参照。

(57) 要約:

高い放電容量とレート特性及びサイクル特性に優れた、リチウムイオン二次電池用正極物質を提供する。

本発明は、組成が $Li_xNi_yMn_zO_2$ (x が $1 + 1/9 \pm (1 + 1/9)$, y が $4/9 \pm (4/9)/10$, z が $4/9 \pm (4/9)/10$) で表され、かつ結晶構造が単斜晶系に属し、空間群が $C12/m1$ (No. 12) であるリチウム-ニッケル-マンガン複合酸化物を正極物質として用いることを特徴とする。本発明のリチウム-ニッケル-マンガン複合酸化物は、さらに単斜晶系の $C12/m1$ (No. 12) で帰属した場合のミラー指数 hkl における (002) 面及び $(13-3)$ 面での $Cu-K\alpha$ 線を用いた粉末X線回折のピーク強度比 $I_{(002)}/I_{(13-3)}$ が 1.35 以上であることが好ましい。